

EVERCOAT[®]

EDGE[™]

SPECIALTY FILLERS



Introducing a revolution in filler technology. Edge Premium Sync[™] is specially formulated to allow for extended work times—up to 40 minutes. Manufacturers and body shop technicians can mix and spread large quantities knowing they have enough time to work large surface areas, saving time and increasing productivity. Edge Premium Sync[™] can also be mixed with Edge Premium[™] body filler for the ultimate flexibility in work time in most any temperature conditions to achieve desired work times at recommended mix ratio.

Product Code	Size	Units/Case	Weight/Case
#200550	16 OZ POUCH	6	8 LBS (3.63 KG)

FEATURES



Flexible Work Time: Designed to allow for extended work times—up to 40 minutes

Formulated with Evercoat's exclusive ECORESIN[™] technology



Industry-leading Evercoat Edge Premium sanding features

BENEFITS

- Technicians can mix and apply an entire gallon reducing the number of steps to cover a large area with less waste and improving productivity
- Patent-pending resin technology made from renewable resources including soy
- Can be applied directly to lightly sanded OEM paint and multiple substrate materials including aluminum, steel, SMC, fiberglass, and lightly sanded OEM painted surfaces
- The ECORESIN[™] family of body filler offers the best sanding capabilities of any other body filler. Period.
- Start with 80 grit sandpaper to help with an estimated 20% or more in sandpaper savings
- Sands the same on day 1 as day 3...or day 10...

EVERCOAT[®]

EDGE[™]


SPECIALTY FILLERS



Benefits of Edge Premium Sync[™]

Large Repair Areas: Mix with Edge Premium to adjust work times so that product can effectively be applied to larger areas

Hot Temperatures: Mix with Edge Premium to extend work times in warmer temperatures without needing to under catalyze



Mix Ratio & Work Time Chart

*Always use 2% hardener. No special hardener required.

MIX RATIO			60°	75°	90°	105°
Edge Premium	Edge Premium Sync [™]					
100%	0%	Work Time	6:00	4:30	2:10	1:15
		Dry Time	22:00	20:00	16:00	14:00
75%	25%	Work Time	17:00	9:00	6:40	3:00
		Dry Time	45:00	33:00	20:00	15:00
50%	50%	Work Time	30:00	20:00	8:45	5:10
		Dry Time	69:00	40:00	22:00	17:00
25%	75%	Work Time	50:00	28:00	14:20	7:45
		Dry Time	110:00	64:00	31:00	20:00
0%	100%	Work Time	80:00	40:00	21:45	13:00
		Dry Time	140:00	110:00	90:00	62:00

