

**PRODUCT:** 2.1 Primer Surfacer

**PART NUMBER:** 102705      Gallon      4 units/case      26 lbs/case

**DESCRIPTION:** **2.1 Primer Surfacer** is a two-component, high-solids primer surfacer that has excellent filling characteristics. This fast drying primer surfacer has excellent gloss holdout and resistance to shrinkage. 2.1 Primer Surfacer sands easily without clogging the sandpaper, while providing excellent resistance to sand scratch swelling.

**SUBSTRATES:**



- Treated Steel
- Treated Aluminum
- Fiberglass/SMC
- OEM Finishes
- Refinish Lacquers, Enamels and Urethanes
- Self-Etch Primers
- Body Filler/Putty


**NOTE:** Steel and Aluminum must be properly treated with an Etch Primer or Metal Etch.

**CLEANING:**



- Surface must be clean and free of dirt, oil, grease and wax
- To solvent clean **raw, exposed fiberglass**, it is recommended to clean exposed area with **acetone**.

**MIXING:**



**5 Parts**      **1 Part**  
 #2705      to      #2712 Fast / 2714 Medium / 2716 Slow  
 2.1 Primer Surfacer      2.1 Primer Catalyst

- Shake and stir the primer and catalyst thoroughly before mixing

Catalyst	Temperature Range
#2712	55°F-75°F/12°C-24°C
#2714	70°F-85°F/21°C-29°C
#2716	80°F (27°C) and above

\*Consider size of repair, air flow and spray conditions with catalyst selection

**POTLIFE:**

15 – 20 minutes @ 70°F (21°C)

- Clean spray gun immediately after use

**APPLICATION:**

- Use a primer gun with a 1.3 to 1.5 fluid nozzle/air cap at a recommended air pressure of 7-8 psi at the cap
- Apply **2-3** medium wet coats allowing **3-5** minutes flash time between coats

**DRYING:**

Air Dry: 2 hours @ 70°F (21°C)  
 Force Dry: 30 min. @ 140°F/60°C (#2716 Slow Catalyst recommended)  
 Dry-to-Sand: 2 hours air dry; upon cool down for force dry.

**NOTE:** Dry times may vary based on film build and ambient air temperature.

**FINISH:**

- Initial Sand: 180 – 320 grit
- Final Sand to Seal: 400 grit
- Final Sand to Topcoat: 600 grit

**TECHNICAL SPECIFICATIONS:**

Appearance	Gray liquid
VOC	Packaged: 2.30lbs/gal (276g/L) Applied: 1.37lbs/gal (164g/L)
Recommended Dry-Film-Thickness (DFT) after Sanding	2.0 – 2.5 mils
Maximum DFT after Sanding	6.0 mils

**SAFETY & HANDLING:**

**IMPORTANT:** The contents of these packages must be mixed with other components before the products can be used. Before opening the packages, be sure to understand the warnings on all labels of all components since the resulting product will have the warnings and cautions of all its parts. Improper spray technique may result in hazardous conditions. Follow the spray equipment manufacturer's instructions to prevent injury or fire. Follow respirator manufacturer's directions for respirator use. Always wear eye and skin protection. Observe all precautions. Consult MSDS for further safety information and/or handling instructions. In case of emergency, contact your local emergency room or poison control center immediately. **For professional use only.**

**EVERCOAT**

a division of Illinois Tool Works Inc. | 6600 Cornell Road | Cincinnati, OH 45242 | (513) 489-7600  
 Made and Printed in the U.S. | ©2012 Evercoat

[evercoat.com](http://evercoat.com)