


PRODUCT: EDGE Short Strand

PART NUMBER: 200564 ½ Gallon 4 units/case 28 lbs/case

DESCRIPTION: **EDGE Short Strand** is a short strand multi-fiber reinforced body repair filler formulated with a combination of Kevlar®. It is ideal for use on metal for finishing welded seams, rusted metal repairs, and repairing composites for filling holes in SMC/Fiberglass, and shattered fiberglass.

APPROVED SUBSTRATES:




- Steel
- Galvanized Steel
- Aluminum
- SMC
- Fiberglass
- Rigid Plastics (ABS, RRIM, Xenoy, etc.)
- Concrete
- Masonry
- Wood

PREPARATION:



- Clean and degrease the entire panel to be repaired with soap and water, followed by a mild cleaning solvent. Surface must be thoroughly dry before repairing or applying material.
- Keep the repair area small. Use 40-80 grit to remove the paint and featheredge.

MIXING:



- Stir the filler before using. Knead the cream hardener.
- Measure hardener 2% by weight (add a ribbon of cream hardener from edge to edge across the center of a 4" diameter puddle).
- Puddles larger than 4" (10 cm) in diameter will require additional hardener. Mix thoroughly until uniform color is achieved.
- Approximate setting time is 5-6 minutes @ 72°F-80°F (22°C)

APPLICATION:



- Apply in layers with even firm pressure.
- Do not apply all at once.

FINISH:



- Sand filler with 80 grit sandpaper.
- If necessary, reapply additional coats, or apply a finish coat of an EDGE Filler or EDGE Putty and follow the recommended sanding procedures.

TECHNICAL SPECIFICATIONS:

- | | |
|--------------------------------------|----------------------------------|
| ▪ Appearance | Green Fibrous Paste |
| ▪ VOC | Packaged: 1.76 lbs/gal (211 g/l) |
| | Applied: 0.41 lbs/gal (49 g/l) |
| ▪ Weight per Gallon | 10.78 lbs/gal. |
| ▪ Sand Time | 10-15 min. |
| ▪ Max Recommended Thickness (sanded) | 1/4 inch (6mm) |
| ▪ Contents and Caution | SDS available upon request |

NOTE: Properties are typical values and should not be considered as sales specifications. Physical testing performed @ ~72°F (22°C) / 75% RH unless otherwise noted.

SAFETY & HANDLING:

Read all directions and warnings prior to using Evercoat® products. Safety Data Sheets can be found online at www.theevercoatedge.com.

NOTES:

Never return mixed filler to can
Keep can closed and store in a cool dry place

USE WITH CREAM HARDENER ONLY!